



PROMETHEUS DEVELOPMENTS LTD.

Unit 9 Langley Park
North Street
Langley Mill
Nottingham
NG16 4BS


Tel: +44 (0)1773 764206
Fax: +44 (0)1773 765048

For the answers you won't have thought of

	Pitchar	Chartek 7	PD71
SG	1.2	1.08	1.02
Rubber Hardness	90	98	92
Adhesion MNM ⁻³	0.09	0.24	0.27
UTS MNM ⁻³	10.63	7.97	12.59
Relative Viscosity Poise	50,000	73,000	13,900

Hydrocarbon Engulfment To 400°C Backface BackFace Insulated

Engulfment test of offshore competitive products



Jet Fire Simulation to 60 Minutes

Jetfire test of current products against PD71

